

AMENDMENTS TO THE CLAIMS

1-7. Cancelled

8. (Original) A fuel cell stack comprising a plurality of planar interleaved fuel cells and interconnects and comprising a contact layer disposed between at least one electrode of a fuel cell and an adjacent interconnect, the contact layer comprising at least two outer layers and a central layer of electrically conductive materials, wherein the central layer comprises a stress relief layer comprised of material selected from the group consisting of:

- (a) particles of a conductive ceramic material which are coarser than in the outer layers;
- (b) particles of a conductive ceramic material which has significantly different sintering characteristics than the outer layers; and
- (c) a porous metallic material.

9. (Original) The fuel cell stack of claim 8 wherein the stress-relief layer comprises coarse particles and the outer layers comprises fine particles.

10. (Original) The fuel cell stack of claim 9 wherein the coarse particles have an average diameter at least about twice as large as the average diameter of the fine particles.

11. (Original) The fuel cell stack of claim 10 wherein the outer layers comprises particles having an average diameter of less than about 2 μm and the central layer comprises particles having a diameter of greater than about 2 μm .

12. (Original) The fuel cell stack of claim 9 wherein the central layer comprises LCN particles.
13. (Original) The fuel cell stack of claim 12 wherein the outer layers comprise LC particles.
14. (Original) The fuel cell stack of claim 8 wherein the outer layers comprise fine LC or LCN particles and the stress relief layer comprises fine LSM particles, or coarse LSM particles, or coarse LCN particles.
15. (Original) The fuel cell stack of claim 14 wherein a first outer layer contacting the electrode comprises fine LCN particles, a second outer layer contacting the interconnect comprises fine LC particles, and the stress relief layer comprises coarse LCN particles.
16. (New) The fuel cell stack of claim 8 wherein any layer of the contact layer comprises a perovskite having the formula ABO_3 where:
- (a) A is a doped or undoped rare earth metal or lanthanide;
 - (b) B is a doped or undoped transition metal; and
 - (c) wherein the perovskite is electrically conductive and has a coefficient of thermal expansion which closely matches that of the fuel cell.
17. (New) The fuel cell stack of claim 16 wherein A comprises doped or undoped lanthanum.
18. (New) The fuel cell stack of claim 17 wherein B comprises cobalt combined with nickel

as follows: $\text{Co}_{1-y}\text{Ni}_y$ where $0.3 \leq y \leq 0.7$.

19. (New) The fuel cell stack of claim 18 wherein the perovskite material comprises $\text{La}_{1-x}\text{E}_x\text{Co}_{0.6}\text{Ni}_{0.4}\text{O}_3$, where E is an alkaline earth metal and x is greater than or equal to zero.

20. (New) The fuel cell stack of claim 16, 17, 18 or 19 wherein at least one dopant is a sintering aid.

21. (New) The fuel cell stack of claim 16 wherein the electrode comprises a noble metal and yttria stabilized zirconia.

22. (New) The fuel cell stack of claim 21 wherein the noble metal comprises palladium.

PLEASE ADDRESS ALL CORRESPONDENCE TO CUSTOMER NUMBER 22828

Dated March 20, 2006.

Respectfully submitted,
Xinge Zhang, et al.
By their Agent



Edward Yoo (Reg. No. 41,435)